

Typical Physical Properties

Pattern: Berkshire

| TEST | UNITS | METHODS | RESULTS |
|-------------------------|--------------|---|---|
| Width | inches (cm) | ASTM D-1776 | 54 (137) |
| Thickness | inches (mm) | ASTM D-1776 | 0.043 (1.1) |
| Weight | O/yd2 (g/m2) | ASTM D-3776 | 15.0 (509) |
| Abrasion #10 Duck Cloth | Double Rubs | Wyzenbeek ASTM D-4157 | 200,000+ |
| Crocking | AATCC Scale | AATCC-8 | 5 dry 5 wet (water) 5 wet (alcohol) |
| Flammability | | UFAC | CLASS I |
| | | NFPA 260-A | CLASS I |
| | | CA TB117-2013 Section 1 | PASS |
| | | ASTM E-84 (adhered) | CLASS A |
| Colorfastness | Light | AATCC-16A | CLASS 5 |
| Emissions | | California 01350 | PASS |
| Hydrolytic Stability | | ISO 1419 : 1995 (E) Method C "Tropical Test" | PASS (15+ Weeks) |
| | | ASTM D 3690-02 | PASS (15+ Weeks) |

Content: 55% TPE, 35% Polyester, 10% Cotton

Features of EnviroLeather™

Durability & Performance

- Resists cracking, peeling, and delamination
- Superior chemical resistance
- Stain resistant, easy to clean and disinfect
- Resists sagging and wrinkling to maintain tight, tailored look
- Outstanding seam abrasion resistance and durability
- Does not support microbial growth when cleaned properly
- Designed for comfort

Environmental & Health Safety Benefits

- PVC-Free, no plasticizers, phthalate-free
- Passes CAL 01350, low VOC emissions
- No added antimicrobial chemicals
- No perfluorochemicals (PFC-Free)
- No flame retardants, bromine-free
- No heavy metals
- Includes recycled and renewable content
- Animal friendly

Disinfecting/Cleaning Information

EnviroLeather™ utilizes a high-tech polymer that results in excellent chemical resistance and cleanability.

Visit www.lidiinteriors.com for complete cleaning instructions and a list of cleaners and disinfectants that we have tested.

Denim Jean Information

EnviroLeather™ was developed to resist permanent staining from denim jeans. Stains that do occur can be easily removed from all of our faux leather collections.